



Your Single Source For Innovative
Architectural Concrete Solutions

BOMANITE CURES, SEALERS AND FINISHES

Cross Reference Guideline

Product Name	Carrier Description	Solids Content	California VOC Content Compliant*	Gloss	Recommended Surfaces	Unique Characteristics	Coverage Per Coat Per Square Foot	Coefficient of Friction (COF)
Bomaseal VOC III	Solvent film forming acrylic	25%	<338 grams/liter Compliant	93 - high gloss (ASTM D523-89)	Exterior only: Bomanite, Bomacron, Toppings, Patène Arctectura, concrete	Premium quality, moderate color enhancement	250-400 porous 300-500 dense	>0.5 dry (ASTM D-2047)
Bomanite Ultra Seal	Solvent film forming acrylic	23%	<334 grams/liter Compliant	93 - high gloss (ASTM D523-89)	Exterior only: Bomanite, Bomacron, Toppings, Patène Arctectura, concrete	High quality, uses an economical solvent blend, moderate color enhancement	250-400 porous 300-500 dense	>0.5 dry (ASTM D-2047)
Bomaseal C-18	Solvent film forming acrylic	18%	<735 grams/liter Non-compliant in California	85 - medium gloss (ASTM D523-89)	Exterior: Bomanite, Bomacron, Toppings, Patène Arctectura, concrete	High quality, lower solids for penetration and lower gloss/build, moderate color enhancement	250-400 porous 300-500 dense	>0.5 dry (ASTM D-2047)
Bomaseal C-27	Solvent film forming acrylic	27%	<680 grams/liter	93 - high gloss (ASTM D523-89)	Exterior: Bomanite, Bomacron, Toppings, Patène Arctectura, concrete	High quality, higher solids for more build/gloss, moderate color enhancement	250-400 porous 300-500 dense	>0.5 dry (ASTM D-2047)
Bomanite HydroLock	Water film forming acrylic/epoxy	22%	<130 grams/liter Compliant	<65 - low gloss (ASTM D523-89)	Interior or exterior: Bomanite, Bomacron, Toppings, Patène Arctectura, masonry units	High quality, water based, epoxy-modified acrylic, minimal color enhancement	150-250 porous 200-400 dense	>0.5 dry (ASTM D-2047)
Bomanite Hydrocoat	Water film forming acrylic	18%	<250 grams/liter Compliant	93 - high gloss (ASTM D523-89)	Interior or exterior: Bomanite, Bomacron, Toppings, Patène Arctectura, concrete	Economical, high quality, solvent based, pure acrylic, moderate color enhancement	600-800 porous 700-1000 dense	>0.6 dry (ASTM D-2047)
Bomanite Color Cure	Water film forming acrylic	23%	<250 grams/liter Compliant	(ASTM D523-89)	Interior or exterior: Bomanite, Bomacron, concrete	Meets or exceeds ASTM C-309 and ASTM C-156 at 300 square feet per gallon, variety of colors	400-500 porous 800+ dense	>0.8 dry (ASTM D-2047)

Product Name	Carrier Description	Solids Content	California VOC Content Compliant*	Gloss	Recommended Surfaces	Unique Characteristics	Coverage Per Coat Per Square Foot Per Gallon	Coefficient of Friction (COF)
Bomanite Clear Cure	Water film forming acrylic	23%	<250 grams/liter Compliant	(ASTM D523-89)	Interior or exterior: Bomanite, Bomacron, concrete	Meets or exceeds ASTM C-309 and ASTM C-156 at 300 square feet per gallon, moderate color enhancement	300-400 porous 400-600 dense	>0.8 dry (ASTM D-2047)
Bomanite Color Wax	Water film forming acrylic	45%	<250 grams/liter Compliant	<40 - satin (ASTM D523-89)	Interior or exterior: Bomanite, Bomacron, Toppings, concrete	High quality, tinted to a wide variety of colors, ease of use, all acrylic formulation, contains no waxes	250 porous 400 dense	>0.5 dry (ASTM D-2047)
Bomanite Interior Floor Finish	Water film forming acrylic	25%	<250 grams/liter Compliant	90 - high gloss (ASTM D523-89)	Interior only: Bomanite, Bomacron, Toppings, Patène Aritectura, concrete.	Intended as a high-gloss maintenance finish over other Bomanite sealers and high performance coatings	1,200 porous 2,000 dense	>0.6 dry (ASTM D-2047)
Bomanite Natural Beauty	Water film forming acrylic	19%	<250 grams/liter Compliant	32 - satin (ASTM D523-89)	Interior only: Bomanite, Bomacron, Toppings, Patène Aritectura, concrete	Intended as a low-gloss maintenance finish over other Bomanite sealers and high performance coatings	1,200 porous 2,000 dense	>0.6 dry (ASTM D-2047)
Bomanite Cure and Seal SB CA Standard	Solvent film forming modified acrylic	25%	< 340 grams/liter Compliant	93 - high gloss (ASTM D523-89)	Exterior: Curing Bomanite, Bomacron, Patène Aritectura, concrete	Intended as a curing compound for fresh concrete. Moderate color enhancement. Formulated with a UV inhibitor to meet ASTM C1315 and C309.	250-400 porous 300-500 dense	>0.5 dry (ASTM D-2047)
Bomanite Cure and Seal SB VOC Standard	Solvent film forming modified acrylic	25%	< 600 grams/liter	93 - high gloss (ASTM D523-89)	Exterior: Curing Bomanite, Bomacron, Patène Aritectura, concrete	Intended as a curing compound for fresh concrete. Moderate color enhancement. Formulated with a UV inhibitor to meet ASTM C1315 and C309.	250-400 porous 300-500 dense	>0.5 dry (ASTM D-2047)

*Before use, consult local, state and federal regulations in your area to make sure product is in compliance.